

Government Of India राष्ट्रीय परीक्षण शाला(पर्वी क्षेत्र)

National Test House (Eastern Region)

११/ १ जजेस कोर्ट रोड , अलीपुर , कोलकाता-७०००२७, 11/1, Judges' Court Road, Alipur, Kolkata - 700 027. ब्लाक- सीपी, सेक्टर- प्र, साल्ट लेक सिटी,कोलकाता- ७०००११, Block - CP, Sector -V, Salt Lake City, Kolkata - 700 091.



परीक्षण प्रमाण पत्र TEST CERTIFICATE (WEB VERSION)

जारी होने की तिथि परीक्षण प्रमाण पत्र सं. कोड नं पृष्ठों की संख्वा पुष्ट Code No Test Certificate No. Date of Issue No of Pages Page NTH(ER)/M(L)/2019/0 21/06/2019 1560244500125 1 0373A

जिसे जारी करना है **Issued To**

VA TECH WABAG LTD.

पता Address

DLF IT Park, Tower 1, 3rd Floor, 8, Major Arterial Road, New Town, Rajarhat,

Kolkata-700156

ग्राहक का सन्दर्भ सं एवं दिनांक Customer's Ref. No.

पंजिका सं एवं दिनांक Register No & Date

WABAG/KRO/10P141/NTH/119/18-19 Dated 15/05/2019

00373/NTH(ER)/M(L)/13/06/2019

परीक्षण सामग्री का विवरण Description of Test Item

Three samples stated as "Reinforcement bars from M/s SPS Steel Rolling Mill Ltd of Elegant Brand, Grade Fe-500 (i) 8mm, (ii) 16mm & (iii) 20mm".

परीक्षण सामग्री का पहचान Identification of Test Item

Emboss mark observed on all three TMT bars as "ELEGANT QST 500D".

नम्ना का विशिष्टि (यदि हीं) Product Specification (Flany)

On the lines of IS 1786:2008 for grade Fe 500.

नम्ना प्राप्ति की तिथि Date of Receipt of the Test Item

11/06/2019

कार्य सम्पादन की तिथि Date(s) of Performance of Tests व्यावद्वत प्रणाली का पहचान Method(s) used for Test

From: 21/06/2019 TO: 21/06/2019

As per IS 1786:2008, IS 1608 (Part-1):2018, IS 1599:2012, IS 228.

नमुना प्रकिया जहाँ प्रासंगिक हों Sampling Procedure where relevant

NA







परीक्षण प्रमाण पत्र **TEST CERTIFICATE** (WEB VERSION)

परीक्षण प्रमाण पत्र सं. Test Certificate No	जारी होने की तिथि Date of Issue	कोड नं Code No	पृष्ठ Page	पृष्ठींकी संख्या No of Pages
NTH(ER)/M(L)/2019/0 0373A	21/06/2019	156024450		3
Sl.No	Test N	lame	Test Result	Limit
1	Mass per m	ietre run, kg	(i) 0.382, (ii) 1.574 & (iii) 2.	41 Pl. see note
2		Stress/ Yield N/sq mm.	(i) 671.9 (ii) 508.2 & (iii) 553.4	500.0 Minimum
3	Percent Elong length 5.65	gation at gauge sqrt area, %.	(i) 731.4, (ii) 588.2 & (iii) 642.0	16.0 Minimum
4		Iandrel Dia as El. 9.3)	(i) 20.0, (ii) 24.0 & (iii) 22.	0 No rupture or cracks visible on the bend portion.
5		Mandrel Dia as ll. 9.4)	(i) Satisfactory, (ii) Satisfactory & (iii) Satisfactory.	No rupture or cracks visible on the rebend portion.



भारत सरकार Government Of India परीक्षण शाला(पूर्वी क्षेत्र) National Test House (Eastern Region)

११/ १ जजेस कोर्ट रोड , अलीपुर , कोलकाता-७०००२७, 11/1, Judges' Court Road, Alipur, Kolkata - 700 027. ब्लाक- सीपी, सेक्टर- ४, साल्ट लेक सिटी,कोलकाता- ७०००९१, Block - CP, Sector -V,Salt Lake City,Kolkata - 700 091.



परीक्षण प्रमाण पत्र **TEST CERTIFICATE** (WEB VERSION)

परीक्षण प्रमाण पत्र सं.	जारी होने की तिथि	कोड नं	पृष्ट	पृष्ठीं की संख्वा
Test Certificate No	Date of Issue	Code No	Page	No of Pages
NTH(ER)/M(L)/2019/0 0373A	21/06/2019	1560244500125	3	3

Test Name Test Result Limit Sl.No

6 0.2% Proof Stress/ Yield (i) Satisfactory, (ii) 500.0 Minimum Stress, N/sq mm. Satisfactory & (iii) Satisfactory.

7 **Chemical Composition.** (i) C-0.14, S-0.024, P-0.060 & As per Clause 4.2 of IS 1786

S+P-0.084; (ii) C-0.12, S-0.021, P-0.056 & S+P-0.077 and (iii) C-0.17, S-0.029, P-0.055 & S+P-0.077

टिपणी

Note

1) Mass per metre (kg), min: (i) 8 mm-0.363, (ii) 16 mm-1.485, (iii) 20 mm-2.37. 2) The tests were conducted during 11.06.19 to 21.06.2019.

केफियत

Remarks

In respect of tests carried out, all the three samples meet the requirements of IS 1786:2008 for Fe 500 Grade.